


# Laying instructions

## P + W flooring boards

WITH PROFILES ON FOUR SIDES



The temperature and relative air humidity during the flooring laying shall be as near as possible to the end conditions in which the flooring shall be laid. Therefore, please make sure that the base and the remaining structure are sufficiently dry. Prior to the laying, the boards shall be conditioned during 2 – 3 days in condition as near as possible to the end conditions in which they will be laid. The boards can be used in dry rooms in which the humidity doesn't exceed 65%. Please, consider the product parameters specified in the product label.

For P6 type boards, thickness 22 mm, to be used in A load category rooms, the distances between beams shall not exceed 600 mm.

The flooring boards shall be laid at right angle on assembly beams. The rows must begin at a different places (as in case of flooring panels). Each board must be so long that it can be fixed to at least 2 assembling beams. At walls and passageways between rooms provide expansion gaps (ca. 10 mm) in order that the flooring can "move". For large areas, 3,5 movement range for one flooring meter is required. Over the gaps, skirting boards shall be applied.

In order to improve the flooring stability, you can glue them together at their joints. In addition, they must be fixed using screws (or nails) to each assembling beam.

In addition:

- ◇ distanced between screws or nails along the walls – 150 - 200 mm, in the middle of the flooring – 250 - 300 mm,
- ◇ distances between screws or nails and board edges – 12 - 15 mm,
- ◇ recommended glue type – all-purpose glue for wood applications.

Prior to the laying please inspect the boards in respect of any deformations, damages or moisture. Damaged or wet boards may not be used.

Please, protect the flooring against any moisture, e.g. during wall painting.



**Kronospan Szczecinek Sp. z o.o.**  
ul. Waryńskiego 1  
PL 78-400 Szczecinek  
tel. +48 94 37 30 100  
fax +48 94 37 30 109  
[www.kronospan.pl](http://www.kronospan.pl)



**Kronospan Mielec Sp. z o.o.**  
ul. Wojska Polskiego 3  
PL 39-300 Mielec  
tel. +48 17 58 22 200  
fax +48 17 58 22 300  
[www.kronospan.pl](http://www.kronospan.pl)

Dimensions	length – 2420 mm	width – 620 mm	thickness – 22 mm
------------	------------------	----------------	-------------------